

Chevaprime A.E.

Penetrating primer

Colours:

Off white or light grey.

Standard Pack:

4 litre cans, 20 litre plastic pails.

Physical Properties:

Liquid Material :

Solids Volume: 35%
Specific Gravity: 1.18
Flash Point: 30°C
Shelf Life: Two years in original containers. Store in cool dry conditions and protect from frost. Some soft settling may occur.

Applied Material:

Adhesion: Excellent penetration and adhesion to flat and corrugated asbestos-cement sheet.

Flexibility: Passes 2 mm mandrel.

Fungus Resistance: **Chevaprime A.E.** contains a highly effective mould resistant additive which contains no toxic metals or phenols.

Surface Preparation:

Large growths of lichen or moss should be carefully removed so as not to disturb asbestos fibres in the ACM. If necessary, vacuum the surface to be coated.

Application Method:

1. Apply by low pressure airless or air assisted spray at 8-10 sqm/litre after thinning 10% by volume with Xylol or Pegasol 100 (Shellsol A).
2. Mist - wet all AGM surface to reduce airborne asbestos contamination.
3. Spray until droplets begin to form on the surface and 'wick-in' occurs to complete penetration.

Dry time:

Touch dry	3-4 hours
Recoat	12-24 hours

Cleanup:

Xylol

Health And Safety:

Eyes and skin should be protected at all times. Respirators approved by NIOSH or OSHA (cartridge type) should be used during **Chevaprime A.E.** application.

Shipping Information:

IMCO Class 3.3 U.N. No. 1263
NZ Dangerous Goods Class 3B

Equus Industries Ltd
PO Box 601
Blenheim
Phone: 03 578 0214 Fax 03 578 0919
Email: admin@equus.co.nz
Web: www.equus.co.nz