

# Traxx 2000 Wearcoat

Elastomeric roof and deck topcoat (smooth or non-skid).

## Key Benefits Summary:

- Formulated for maximum exterior durability.
- Very good resistance to cleaning chemicals and chemical splashes.
- Easy to maintain and recoat if damaged.
- Gloss level can be varied to suit end use.

## Limitations:

- Bright colours may require additional coats for full opacity
- May be slow curing under adverse circumstances.
- Has a low film build - it is designed as a topcoat only for elastomeric membrane systems.

## Colour:

Available in most BS2660 and BS5252 colours. Minimum quantity restrictions may apply for matched colours.

## Standard Pack:

1 and 4 litre units (prebatched)

## Physical Properties:

Liquid Material:	Unit A	Unit B
Solids (% by volume):	49%	47%
Specific Gravity:	1.25	1.01
Flash Point:	32°C	32°C
Shelf Life:	3 years	2 years

## Applied Film: (Traxx 2000 with Wearcoat)

Flexibility:	Passes 3mm mandrel @ 500µ d.f.t.
Elongation:	>250% at break
Tear Strength:	>3.5N/mm
Durability:	Excellent.
Adhesion:	Very good with correct priming system
Chemical Resistance:	Excellent resistance to treated and waste water. Dilute acids and alkalis, salts etc. general process wastes.
Abrasion Resistance:	Excellent.

## Surface Preparation:

All surfaces must be clean and dry at time of application. For most applications priming is not mandatory ie.

Porous surfaces:	<b>Traxx Primer 1070</b> at 10sqm/litre
Dense concrete:	<b>Traxx Primer 1050</b> at 10sqm/litre
Contaminated, previously painted & timber surfaces:	<b>Chevaline Epistix</b> at 8sqm/litre
Steel:	<b>Protexx Zincure</b> at 12sqm/litre

## Specification Notes:

Refer to individual **Traxx 2000** system specifications for full details.

## Areas Of Use:

A liquid-applied trafficable elastomeric topcoat (smooth or non-skid) for use on roofs, decks, pool surrounds and walkways.

## Product:

A two-component solvent-borne flexible aliphatic polyurethane lacquer available in either smooth or non-skid finish, depending on service conditions.

## Application Properties:

### Spreading rate: (per coat)

Theoretical:	12.25m <sup>2</sup> /litre (40µ dft) - smooth
Practical:	10m <sup>2</sup> /litre (40µ dft) - smooth
	8m <sup>2</sup> /litre - non slip

### Recommended film build:

Reinforced systems	35-40 µ / coat
Unreinforced systems	35-40 µ / coat

### Dry time:

Touch dry	2-6 hours
Through dry	8-20 hours

### Pot life:

4-8 hours

**Thinning/Clean up:** Colourcure AP Thinners

## Application Method:

Mix unit B into unit A, ensuring complete homogeneity (3-4 minutes with a drill and beater). Apply direct from mixed can by brush, roller or spray. Thin with **Colourcure AP Thinners** as needed for easy spreading.

## Health And Safety:

These materials are solvent-based urethane coatings. All normal precautions for handling solvent-borne materials must be observed including:

- Storage in cool dry conditions away from naked flames.
- No smoking in area while handling or applying Traxx 2000 Wearcoat.
- Use barrier cream on exposed skin.
- Use of solvent cartridge mask and safety goggles while handling material.

Note that these materials contain less than 0.2% free isocyanate monomer and presents a low health hazard, but in some countries special regulations may pertain.

## Transport Classification:

UN No. 1263  
IMW Classification 3.3

## Equus Industries Ltd

PO Box 601

Blenheim

Phone: 03 578 0214 Fax 03 578 0919

Email: [admin@equus.co.nz](mailto:admin@equus.co.nz)

Web: [www.equus.co.nz](http://www.equus.co.nz)