

# CHEVALINE SPRAYTEXX-G

## High-build sprayed texture finish

April 2024

### PURPOSE AND AREAS OF USE:

A high-build “lumpy” sprayed texture finish, for use in all interior and exterior situations. Sprayed effect can be varied to suit aesthetic and service requirements. Spraytexx-G can be applied to all stable building materials over appropriate primer and finished with one of a range of topcoats depending on service condition.

### PRODUCT:

An aggregate-filled thixotropic waterborne acrylic material. Is tough and durable with high adhesion, fast drying and early water resistance.

### PROCESS COMPATIBILITY:

Use with Coverall 50/50, Blockfil or Coverfil primers depending on surface to be coated. The following Chevaline topcoats can be used over Spraytexx-G:

Coverall	Colourglaze
Covercryn	Extracover
Colourcure	

### COLOURS:

Available in all BS5252 colours. Light pastels and bright colours will not match exactly because of aggregate content.

### STANDARD PACK:

15 litre pail.

### PHYSICAL PROPERTIES:

Liquid Material	
Solids (% by volume)	70%
Specific gravity	1.5-1.55
Flash point	None - waterborne system.
Shelf life	Two years in original sealed pails when stored in cool dry conditions.

Applied Film	
Flexibility	Passes 5 mm mandrel.
Durability	Very good weather resistance. System life depends on topcoats selected for use.
Adhesion	Excellent adhesion to recommended primers.
Chemical resistance	Very good to normal atmospheric pollutants. System resistance will depend on topcoat properties.
Fungus resistance	Spraytexx-G contains a highly effective mould resistant additive which does not contain toxic metals or phenols.

### SURFACE PREPARATION:

All surfaces must be clean, dry and continuous at the time of coating application. In exterior situations waterblast surface if practical and/or necessary to remove existing loose paint, surface dirt and unsound material. All interior building boards shall be fixed, taped and stopped according to board makers instructions. All masonry block surfaces shall be de-nibbed and/or patched using Chevaline Troweltexx, and neatly tuck or flush pointed as required. Where moving joints are to be installed refer to Equus for advice on the particular application and circumstances.

Cellulose fibre/Hardiflex joints shall be taped according to instructions provided to Approved Equus Contractors.

# CHEVALINE SPRAYTEXX-G

## High build sprayed texture finish

April 2024

### PRIMING:

Harditex boards, cement plaster and "tight" concrete surfaces	Coverall 50/50 primer applied by brush at 9-10 sqm/litre.
Masonry block and "open" off-form concrete	Blockfil or Coverfil. Primer type and spreading rate at 3-5 sqm/litre dictated by surface profile.
Gypsum plaster board	Chevaline PBT Primer applied by brush or roller at 8-9 sqm/litre.

### APPLICATION PROPERTIES:

**Spreading rate:** 0.7-1 sqm/litre (10.5-15 sqm/15 litre pail) depending on texture required.

### Dry times (Under normal conditions):

Touch dry	1-2 hours
Through dry	12-24 hours
Full hardness	7-10 days

### Recoat times:

Waterborne topcoats	8-12 hours
Solvent-borne topcoats	24-48 hours, allow up to 72 hours in winter.

### Spray setup:

Hopper gun or mono-pump texture gun air pressure 50-60 p.s.i. Nozzle size 4-8mm dia. depending on required texture.

### SPECIFICATION NOTES:

- Spraytexx-G is not generally recommended in areas of high pollution fallout where the highly textured surface may retain unsightly pollutants and dirt.
- While masking is still in place an appropriate Chevaline Topcoat shall be applied. Advice should be sought from the Manufacturer as to the appropriate topcoat for the service conditions.

### MAINTENANCE:

Topcoats should be checked for recoating on a 7-10 year cycle for exterior use and 10 year cycle for interior use. Clean when required using low-medium pressure spray and a dilute neutral detergent solution.

If topcoats are renewed whilst film is still sound, the life of the system will be easily prolonged for further similar cycle periods.

### WARNINGS AND BANS:

Is the building product/building product line subject to warning or ban under section 26 of the Building Act 2004?	No
--	----

### MANUFACTURERS CONTACT DETAILS:

Manufacture location	New Zealand
Legal and trading name of manufacturer	Equus Industries Ltd.
Manufacturer address for service	4 Sheffield Street, Blenheim 7274
Manufacturer website	www.equus.nz
Manufacturer email	info@equus.nz
Manufacturer phone number	03 578 0214
Manufacturer NZBN	9429032000306